

## 2-2125: W1000 PVC Rough Top - Hi

Color: White

Plies: 1

Nom. OAG: 0.31" +/- 0.03"

Recessed OAG: 0.12"

Fabric: Interwoven Polyester

**Top Surface:** Hemp Impression Rough

Top

**Bottom Surface:** Friction Surface

Compound: PVC

Work Tension: 100 lbs./PIW Elongation: Less than 2%

Weight: 0.1 lbs./PIW

Minimum Pulley: 3"

**Backflex Min. Pulley Dia.:** 4.5" **Working Temp. (F):** 0 to 180

Max. Stocked Width: 72"

**Attributes:** Sliderbed Suitable

**Features:** 2-2125 features the popular interwoven carcass with a hemp impression rough top cover. Refer to the chemical resistance chart when choosing a cleaning solution. NOTE--The rough top impression must be recessed to use lacing. Use Recessed OAG for Lacing Recommendation. W1000 PVC Rough Top-HI can be used as a general purpose incline belt where the incline is moderate. It is FDA compliant for use in some food applications.


Warning: Trying to access array offset on value of type bool in /home/mulhernbelting/public\_html/staging.mulhernbelting.com/wp-content/plugins/elementor-pro/modules/dynamic-tags/tags/post-featured-image.php on line 39



## **Splicing Instructions**

Part Number: 2-2125 Part Description: W1000 PVC Rough Top - Hi





Finger Length (A):

Finger Width (B):

| Imperial | Metric       |
|----------|--------------|
| 3"       | 76 <b>mm</b> |
| 3/4"     | 19 <b>mm</b> |

## **Water Cooled**

## **Hi-Speed**

**Upper Platen Temp:** 

**Bottom Platen Temp:** 

**Pressure:** 

Time:

| Imperial         | Metric           | Imperial         | Metric           |
|------------------|------------------|------------------|------------------|
| 340° <b>F</b>    | 171 ° <b>C</b>   | 330 ° <b>F</b>   | 166 ° <b>C</b>   |
| 340° <b>F</b>    | 171 ° <b>C</b>   | 330 ° <b>F</b>   | 166 ° <b>C</b>   |
| 50 <b>PSI</b>    | 3.4 <b>bar</b>   | 36 <b>PSI</b>    | 2.5 <b>bar</b>   |
| 01:00 <b>m:s</b> | 01:00 <b>m:s</b> | 03:00 <b>m:s</b> | 03:00 <b>m:s</b> |

|   | Press Layout | Description                                    | Part # to Order |
|---|--------------|--|-----------------|
| _ | 225          | Top Heating Platen with equalizing plate       |                 |
| Г |              | Impression Pad                                 |                 |
|   |              | Meltable Foil (optional)                       | 8340C           |
|   |              | Belt   | 2-2125          |
|   |              | Teflon   | 6-3000          |
|   | 722          | Bottom Heating Platen<br>with equalizing plate |                 |

For high stress applications splice with reinforcing fabric.

Ph: (800) 253-6300 Fax: (201) 337-6540 sales@mulhernbelting.com www.mulhernbelting.com