



(800) 253-6300

sales@mulhernbelting.com

www.mulhernbelting.com

3-1313: 3 Ply Blue R/T

Color: Blue

Plies: 3

Nom. OAG: 0.313" +/- 0.02"

Recessed OAG: 0.16"

Fabric: Polyester

Top Surface: Hemp Impression Rough
Top

Bottom Surface: Skim

Compound: XNBR

Work Tension: 150 lbs./PIW

Elongation: Less than 2%

Weight: 0.12 lbs./PIW

Minimum Pulley: 2.5"

Working Temp. (F): 0 to 250

Max. Stocked Width: 72"

Attributes: Abrasion Resistant

Top Cover Coefficient of Friction: 1.2

Bottom Cover Coefficient of Friction:
0.3

Features: The Carboxylated Nitrile Compound has been proven to out perform even Urethane in wear resistance and at the same time have oil resistance. The belt will normally out last SBR or neoprene roughtops. NOTE: The roughtop profile must be recessed to use lacing. Use Recessed OAG for Lacing Recommendation. 3 Ply Blue Roughtop is particularly popular in the paper and cardboard box industries. It is also popular in any application where any high abrasive or oily conditions exist.

Warning: Trying to access array
offset on value of type bool in
/home/mulhernbelting/public_html/staging.mulhernbelting.com/wp-
content/plugins/elementor-
pro/modules/dynamic-
tags/tags/post-featured-image.php
on line 39